



Product Data Sheet

PRODUCT DESCRIPTION

70702/70703 is a two component 100% solids epoxy used to re-surface deteriorated concrete, leaving a smooth, durable finish. This product is ideal for use on spalled or damaged concrete floors to level, prime or seal the concrete substrate. It is not designed as an exposed surface and must be topcoated.

PRODUCT USE

A general purpose re-sealer for concrete surfaces.

PRODUCT NUMBERS AND COLORS

Standard colors are: 70702 (Epoxy Resin) Light Yellow
70703 (Hardener) Gray

CURED FILM PERFORMANCE

Description	Test Method	Results
Tensile Strength	ASTM D2370	4,500 - 5,500 psi
Elongation	ASTM D2370	3 - 8%
Compressive Strength	ASTM D695	25,875 psi
Flexural Strength	ASTM D790	1,398 psi
Flexural Modulus	ASTM D790	73,480 psi

The above tested results are typical values. Individual lots may vary up to 10% from the typical value.

PRODUCT DATA

Description	Results
Viscosity (70702)	9,000 - 10,000 cps
Viscosity (70703)	12,000 - 22,000 cps
Pot Life (mixed)	1 hour
Shore D	85 @ 7 days at 135°F
Dry to Touch	6 hours
Impact Resistance	24 in/lbs @ 10 mils DFT
Reverse Impact	8 in/lbs @ 10 mils DFT
Sag Resistance	10 mils
Adhesion	Excellent recoat adhesion with urethanes or epoxies.

The above tested results are typical values. Individual lots may vary up to 10% from the typical value.

APPLICATION

Mix 1:1 by volume to a thixotropic spreading suspension. Mixed color is light gray. Do not tint material. Mixed viscosity increases from initial viscosity until full cure.

Sand or walnut shells may be broadcast into wet product to develop a texture. For grout applications, mix may be blended with up to 4 parts sand by volume.

May be applied between 40°F and 100°F.

STORAGE

Containers should be stored in a cool (70°F) area to insure long shelf life.

HEALTH AND SAFETY

Read the Material Safety Data Sheet (MSDS) and container labels for detailed health and safety information. This product is intended for industrial use by properly trained professional applicators only.

The information, data and suggestions contained herein are believed to be reliable, based upon our knowledge and experience; however, it is expressly declared that Seller does not guarantee the result to be obtained in Buyer's process. **SELLER HEREBY EXPRESSLY DISCLAIMS ANY IMPLIED WARRANTY OF MERCHANTABILITY FOR FITNESS FOR A PARTICULAR PURPOSE AND/OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED** as to any and all products and/or suggestions described herein, whether such products are used alone or in combination with other materials. Buyer must make its own determination of the suitability of any product for its use, and the completeness of any information contained herein. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. Applicator is an independent contractor of, and should under no circumstances be viewed as an employee or agent of, the NEOGARD® Division of JONES-BLAIR®. 10122008/70702-70703PD.indd