



Product Data Sheet

PRODUCT DESCRIPTION

7261 is a high solids, fire retardant, quick-set elastomeric acrylic coating for application over polyurethane foam, concrete, wood, metal, masonry and other types of properly prepared surfaces. This coating is not designed for use on roofs that have any ponding water.

PRODUCT NUMBERS AND COLORS

Standard color: White

CURED RESIN PERFORMANCE

Description	Test Method	Results
Tensile Strength	ASTM D2370	280 psi
Elongation	ASTM D2370	270%
Permanent Set	ASTM D412	<20%
Water Resistance	ASTM D471	<20%
MVT @ 30 mils	ASTM E96	2.9 English
Adhesion	ASTM D903	5 lb/in

PRODUCT DATA

Description	Test Method	Results
Weight/Gal	ASTM D1475	11.5 lbs/gal
Weight Solids	ASTM D4209	63%
Volume Solids	Calculated	50%
VOC	EPA Method 24	38 g/L
Viscosity	ASTM D562	105 KU
Flash Point	ASTM D3278	None
Red Label		No
Pot Life		N/A
Shelf Life		1 year
Cure Time @ 75°F, 50% RH		1 - 2 hrs

LIMITATIONS AND PRECAUTIONS

Do not apply 7261 at temperatures below 50°F, or when there is a possibility of temperatures falling below 32°F within a 12 hour period after application.

7261 requires complete evaporation of water to cure. Cool temperatures and high humidity retard cure. Do not apply if weather conditions will not permit complete cure before rain, dew, or freezing temperatures occur. Do not apply in the late afternoon if heavy condensation may appear during the night.

THINNING AND CLEANUP

Thinning of materials is not required under normal application conditions. However, if required, thin material with water. Never thin more than 10% without consulting NEOGARD®.

Water should be used for cleaning equipment.

STORAGE

Drums and cans of coating material should be stored in a cool (75°F) area.

WARNING!

Protect Material from Freezing.

7261 will freeze and become unusable at temperatures below 32°F.

HEALTH AND SAFETY

Read the Material Safety Data Sheet (MSDS) and container labels for detailed health and safety information. This product is intended for use by properly trained professional applicators only.

The information, data and suggestions contained herein are believed to be reliable, based upon our knowledge and experience; however, it is expressly declared that Seller does not guarantee the result to be obtained in Buyer's process. **SELLER HEREBY EXPRESSLY DISCLAIMS ANY IMPLIED WARRANTY OF MERCHANTABILITY FOR FITNESS FOR A PARTICULAR PURPOSE AND/OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED** as to any and all products and/or suggestions described herein, whether such products are used alone or in combination with other materials. Buyer must make its own determination of the suitability of any product for its use, and the completeness of any information contained herein. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. Applicator is an independent contractor of, and should under no circumstances be viewed as an employee or agent of, the NEOGARD® Division of JONES-BLAIR®. 071707/7261HTPD.indd

NEOGARD®

Div. of JONES-BLAIR®

2728 Empire Central - P.O. Box 35286 - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com