



Product Data Sheet

PRODUCT DESCRIPTION

Odor Free Urethane II is a single component (plus 7923 accelerator) moisture-cured, aromatic, polyurethane coating designed for use as a waterproofing membrane for pedestrian and vehicular traffic bearing surfaces. Mix ratio is 60:1 by volume with 7923.

PRODUCT NUMBERS AND COLORS

Standard colors are: 7430-02 Gray
7435-02 Tan

CURED RESIN PERFORMANCE

Description	Test Method	Results
Tensile Strength	ASTM D412	2,500 psi
Elongation	ASTM D412	400%
Permanent Set	ASTM D412	15%
Tear Resistance	ASTM D1004	250 lb/in
Water Resistance	ASTM D471	2.5%
MVT @ 30 mils	ASTM E96	1.3 English
Taber Abrasion	ASTM D4060	15 mg/1,000 cs17
Shore A	ASTM D2240	77-85
Adhesion	ASTM D903	30 pli

The above tested results are typical values. Individual lots may vary up to 10% from the typical value.

PRODUCT DATA

Description	Test Method	Results
Weight/Gal (mixed)	ASTM D1475	10.22 lbs/gal
Weight Solids (mixed)	ASTM D4209	81.7%
Volume Solids (mixed)	Calculated	73.6%
VOC (mixed)	EPA Method 24	226 g/L
Viscosity (mixed)	ASTM D562	>95 KU
Flash Point	ASTM D3278	125°F

The above tested results are typical values. Individual lots may vary up to 10% from the typical value.

MIXING

Read container labels, MSDS and application instructions prior to mixing. Mix 5 gallon pails and 55 gallon drums with a variable speed drill utilizing a jiffy mixer to suspend any settled pigment and attain a uniform color. Time will vary depending on temperature conditions.

STORAGE

Containers of polyurethane coating should be stored in a cool (70°F) area to insure long shelf life. To prevent container rupture due to very high temperature, keep away from heat and/or open flames.

HEALTH AND SAFETY

Read the Material Safety Data Sheet (MSDS) and container labels for detailed health and safety information. This product is intended for industrial use by properly trained professional applicators only.

The information, data and suggestions contained herein are believed to be reliable, based upon our knowledge and experience; however, it is expressly declared that Seller does not guarantee the result to be obtained in Buyer's process. **SELLER HEREBY EXPRESSLY DISCLAIMS ANY IMPLIED WARRANTY OF MERCHANTABILITY FOR FITNESS FOR A PARTICULAR PURPOSE AND/OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED** as to any and all products and/or suggestions described herein, whether such products are used alone or in combination with other materials. Buyer must make its own determination of the suitability of any product for its use, and the completeness of any information contained herein. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. Applicator is an independent contractor of, and should under no circumstances be viewed as an employee or agent of, the NEOGARD® Division of JONES-BLAIR®. 04232009/7430-02PD.indd

NEOGARD®
Div. of JONES-BLAIR®

2728 Empire Central - Dallas, Texas 75235 - Toll Free (800) 321-6588 - Fax (214) 357-7532 - www.neogard.com