



Product Data Sheet

PRODUCT DESCRIPTION

7922 is a vertical additive for wide variety of urethane to enhance the sag resistant properties of the coating material.

PRODUCT NUMBER AND COLOR

Standard color: 7922 Amber

USAGE CHART

7922 can be used for the following urethane coating products with a 30 minute induction time.

Products	7922/5 gals	Sag Resistance (mls)
7401	1/2 pint	16 - 18
7425	2 x 1/2 pints	14 - 16
7430	2 x 1/2 pints	14 - 16
7435	2 x 1/2 pints	14 - 16
7441	2 x 1/2 pints	14 - 16
7442	2 x 1/2 pints	14 - 16
7443	2 x 1/2 pints	14 - 16
7419	1/2 pint	16 - 18
70611	1/2 pint	>50
70612	1/2 pint	>50
70613	1/2 pint	>50
70620	1/2 pint	>50
70405	1/2 pint	12 - 14
70410	1/2 pint	14 - 16

PRODUCT DATA

Description	Test Method	Results
Weight/Gal	ASTM D1475	9.1 lbs/gal
Weight Solids	ASTM D4209	100%
Volume Solids	Calculated	100%
VOC	EPA Method 24	0.0 g/L
Viscosity	ASTM D2196	100 cps
Flash Point	ASTM D3278	250+°F
Pot Life (mixed with urethane coating @ 75°F and 50% RH)	Calculated	90 - 120 minutes
Shelf Life		1 year
Cure Time @ 75°F and 50% RH	TT-S-00230A	24 hrs

The above tested results are typical values. Individual lots may vary up to 10% from the typical value.

HEALTH AND SAFETY

Before using this product, carefully read the Material Safety Data Sheet (MSDS) and container labels for detailed health and safety information. This product is intended for industrial use by properly trained professional applicators only.

The information, data and suggestions contained herein are believed to be reliable, based upon our knowledge and experience; however, it is expressly declared that Seller does not guarantee the result to be obtained in Buyer's process. **SELLER HEREBY EXPRESSLY DISCLAIMS ANY IMPLIED WARRANTY OF MERCHANTABILITY FOR FITNESS FOR A PARTICULAR PURPOSE AND/OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED** as to any and all products and/or suggestions described herein, whether such products are used alone or in combination with other materials. Buyer must make its own determination of the suitability of any product for its use, and the completeness of any information contained herein. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. Applicator is an independent contractor of, and should under no circumstances be viewed as an employee or agent of, the NEOGARD® Division of JONES-BLAIR®. 041508/7922PD.indd

NEOGARD®

Div. of JONES-BLAIR®

2728 Empire Central - P.O. Box 35286 - Dallas, Texas 75235 - Toll Free (800) 321-6588 - Fax (214) 357-7532 - www.neogard.com