

**Guide Specification****PART 1 GENERAL****1.1 SUMMARY**

- A. Provide labor, materials, equipment and supervision necessary to install a fluid-applied vehicular traffic coating system as outlined in this specification to new or existing concrete surfaces.
- B. The manufacturer's application instructions for each product used are considered part of this specification and should be followed at all times.
- C. Related Sections:
 - 1. Section 03 30 00 - Cast-in-Place Concrete
 - 2. Section 03 40 00 - Precast Concrete
 - 3. Section 07 90 00 - Joint Protection

1.2 SYSTEM DESCRIPTION

- A. AUTO-GARD® shall be a complete system of compatible materials supplied by NEOGARD® to create a seamless waterproof membrane.
- B. AUTO-GARD® shall be designated for application on the specific type of deck indicated on the drawings.

1.3 SUBMITTALS

- A. Product Data: Submit NEOGARD® product literature and installation instructions.
- B. Project Reference List: Submit list of projects as required by this specification.
- C. Samples: Submit samples of specified vehicular traffic coating system. Samples shall be construed as examples of finished color and texture of the system only.
- D. Applicator Approval: Submit letter from manufacturer stating applicator is approved to install the vehicular traffic coating system.
- E. Warranty: Submit copy of manufacturer's standard warranty.

1.4 QUALITY ASSURANCE

- A. Supplier Qualifications: AUTO-GARD®, as supplied by NEOGARD®, is approved for use on this project.

- B. Applicator Qualifications: Applicators shall be approved to install specified system.
- C. Requirement of Regulatory Agencies:
 - 1. The vehicular traffic coating system shall be rated Class "A" by Underwriters Laboratories (ASTME108/UL790). Containers to bear Underwriters Laboratories labels.
 - 2. Materials used in the vehicular traffic coating system shall meet existing Federal, State and local VOC regulations.

1.5 DELIVERY, STORAGE AND HANDLING

- A. Delivery: Materials shall be delivered in original sealed containers, clearly marked with supplier's name, brand name and type of material.
- B. Storage and Handling: Recommended material storage temperature is 75°F. Handle products to avoid damage to container. Do not store for long periods in direct sunlight.

1.6 JOB CONDITIONS

- A. Environmental Conditions:
 - 1. Do not proceed with application of materials when deck temperature is less than 40°F.
 - 2. Do not apply materials unless surface to receive coating is clean and dry, or if precipitation is imminent.

1.7 WARRANTY

- A. Upon request, NEOGARD® shall offer the manufacturer's standard warranty upon receipt of a properly executed warranty request form.

PART 2 PRODUCTS**2.1 MANUFACTURER**

- A. NEOGARD® Division of JONES-BLAIR® Company, P.O. Box 35286, Dallas, TX 75235, Toll Free (800) 321-6588, Fax (214) 357-7532, www.neogard.com.

2.2 MATERIALS

- A. Vehicular Traffic Coating Material:
 - 1. Primer: Concrete and metal primers as required by NEOGARD®.
 - 2. Flashing Tape: 86218 flashing tape (ETERNABOND™ WebSeal™) or approved equal having a minimum thickness of 30 mils.
 - 3. Liquid Flashing: 70410 or 7430 series polyurethane coating.
 - 4. Aggregate: 7992 silica (quartz) sand or other aggregate approved by NEOGARD®.
 - 5. Elastomeric Base Coat: 70410 polyurethane coating, gray in color.

6. Elastomeric Topcoat: 7400 series polyurethane coating, gray or tan in color.
7. Sealant: 70991 or other polyurethane sealant approved by NEOGARD®.

2.3 MATERIAL PERFORMANCE CRITERIA

- A. Physical properties of cured vehicular traffic coating system used on this project are:

PERFORMANCE REQUIREMENTS OF CURED FILM			
PHYSICAL PROPERTIES	TEST METHOD	BASE COAT	TOPCOAT
Tensile Strength	ASTM D412	1,200 psi	2,500 psi
Elongation	ASTM D412	400%	400%
Permanent Set	ASTM D412	<10%	<30%
Tear Resistance	ASTM D1004	150 pli	200 pli
Water Resistance	ASTM D471	<3% @ 7 days	<3% @ 7 days
MVT @ 20 mils	ASTM E96	2.6 English	2 English
Taber Abrasion (cs17), max	ASTM D4060	30 mg/1,000 rev	25 mg/1,000 rev
Shore A	ASTM D2240	70-75	75-80
Adhesion	ASTM D4541	300 psi	300 psi
Weathering Resistance	ASTM D822	N/A	Slight Chalk
Thermal Shock	Alternate Heat/Cold	No Loss of Adhesion	No Loss of Adhesion
"Standard Specifications for High Solids Content, Cold-Applied Elastomeric Waterproofing Membrane with Integral Wearing Surface"	ASTM C957	System Exceeds Requirements	

2.4 ACCESSORIES

- A. Miscellaneous materials such as cleaning agents, adhesives, backer rod, deck drains, etc. shall be a composite part of the deck system and shall be compatible with the specified vehicular traffic coatings.

PART 3 EXECUTION

3.1 EXAMINATION

- A. Concrete: Verify that the work done under other sections meets the following requirements:
1. That the concrete deck surface is free of ridges and sharp projections. If metal forms or decks are used they should be ventilated to permit adequate drying of concrete on exterior exposed deck.
 2. That the concrete was cured for a minimum of 28 days. (Minimum of 4,000 psi compressive strength). Water-cured treatment of concrete is preferred. The use of concrete curing agents, if any, shall be of the sodium silicate base only; others require written approval by NEOGARD®.
 3. That the concrete was finished by a power or hand steel trowel followed by soft hair broom to obtain light texture or "sidewalk" finish.
 4. That damaged areas of the concrete deck be restored to match adjacent areas. Use 100% solids epoxy and sand for filling and leveling.

3.2 PREPARATION

- A. Surface Preparation:

1. Cleaning: Surfaces contaminated with oil or grease shall be vigorously scrubbed with a power broom and a strong non-sudsing detergent. Thoroughly wash, clean, and dry. Areas where oil or other contaminants penetrate deep into the concrete may require removal by mechanical methods.
2. Shot Blasting: Required surface preparation method for remedial construction, is also the preferred method for new construction. Mechanically prepare surface by shot blasting to industry standard surface texture (ICRI's CSP3-4) without causing additional surface defects in deck surface. Shot blasting does not remove deep penetrating oils, grease, tar or asphalt stains. Proper cleaning procedures should be followed to insure proper bonding of the deck coating. Note: If shot blasting is not practical, treat concrete surfaces with 10% to 15% solution of muriatic acid to remove laitance and impurities. After acid has stopped foaming or boiling, immediately rinse thoroughly with water. Re-rinse as required to remove muriatic acid solution. Acid etching does not remove deep penetrating oils, grease, tar or asphalt stains. Proper cleaning procedures should be followed to insure proper bonding of the deck coating.
3. Cracks and Cold Joints: Visible hairline cracks (up to 1/16" in width) in concrete and cold joints shall be cleaned, primed as required and treated with liquid flashing a minimum distance of 2" on each side of crack to yield a total thickness of 30 dry mils. Large cracks (over 1/16" in width) shall be routed and sealed with sealant. Sealant shall be applied to inside area of crack only, not applied to deck surface. Detail sealed cracks with liquid flashing a distance of 2" on each side of crack to yield a total thickness of 30 dry mils.
4. Control Joints: Seal secondary control joints with sealant. Sealant shall be applied to inside area of joint only, not applied to deck surface. Detail sealed joints with liquid flashing a distance of 2" on each side of joint to yield a total thickness of 30 dry mils.
5. Flashing Tape: Install flashing tape where indicated on the drawings prior to the application of elastomeric coating.
6. Surface Condition: Surface shall be clean and dry prior to coating.

3.3 APPLICATION

- A. Seed and Lock Method
1. Primer: Where required, apply 1/3 gallon per 100 square feet (300 sf/gal) to all concrete surfaces in strict accordance with procedures outlined by NEOGARD®. Within 24 hours of application of primer, base coat must be applied. If base coat cannot be applied within 24 hours, reprime.
 2. Base Coat: Apply 1-2/3 gallons per 100 square feet (60 sf/gal) of elastomeric base coat to deck surfaces in strict accordance with procedures outlined by NEOGARD®. Extend base coat over cracks and control joints which have received treatment.
 3. Wearing Surface Coat: Apply 2/3 gallon per 100 square feet (150 sf/gal) of elastomeric topcoat in strict accordance with procedures outlined by NEOGARD® and immediately broadcast aggregate, evenly distributed, into wet coating at the rate of 10 to 15 pounds per 100 square feet.

4. Finish Coat: When dry, remove excess aggregate and recoat surface with 1 gallon per 100 square feet (100 sf/gal) of elastomeric topcoat in strict accordance with procedures outlined by NEOGARD®. Total system coating thickness averages 40 dry mils exclusive of aggregate.
5. Double-Texturing: For heavy traffic areas such as ticket booths, spiraled ramps, turn areas, or in other areas subjected to extremely high traffic abrasion, double-texturing is required. In such areas, apply double-texture as follows: After the wearing surface coat to receive aggregate has cured and loose aggregate removed, apply 1 gallon per 100 square feet (100 sf/gal) of elastomeric topcoat in strict accordance with procedures outlined by NEOGARD® and immediately broadcast additional aggregate, evenly distributed, into wet coating at the rate of 10 to 15 pounds per 100 square feet. When dry, remove excess aggregate and recoat surface with 1 gallon per 100 square feet (100 sf/gal) of elastomeric topcoat in strict accordance with procedures outlined by NEOGARD®. Double-textured areas will yield an average of 52 dry mils exclusive of aggregate.

*Note to specification writer: Thickness values of cured film are averages and can vary due to finish of surface.

B. Seed and Backroll Method

1. Primer: Where required, apply 1/3 gallon per 100 square feet (300 sf/gal) to all concrete surfaces in strict accordance with procedures outlined by NEOGARD®. Within 24 hours of application of primer, base coat must be applied. If base coat cannot be applied within 24 hours, reprime.
2. Base Coat: Apply 1-2/3 gallons per 100 square feet (60 sf/gal) of elastomeric base coat to deck surfaces in strict accordance with procedures outlined by NEOGARD®. Extend base coat over cracks and control joints which have received treatment.
3. Heavy Duty Areas (Turns, ramps, etc.): Apply 1 gallon per 100 square feet (100 sf/gal) of elastomeric topcoat in strict accordance with procedures outlined by NEOGARD® and immediately broadcast aggregate, evenly distributed, into wet coating at the rate of 10 to 15 pounds per 100 square feet. Note: For parking stalls and non-heavy duty service, skip this step and proceed to item #4.
4. Topcoat: When previous coating application is dry, recoat surface with 1-2/3 gallons per 100 square feet (60 sf/gal) of elastomeric topcoat and immediately broadcast aggregate at a rate of approximately 15 to 18 pounds per 100 square feet and backroll to

encapsulate aggregate. Total system coating thickness for heavy duty areas will average 52 dry mils exclusive of aggregate. All other areas will average 40 dry mils exclusive of aggregate.

*Note to specification writer: Thickness values of cured film are averages and can vary due to finish of surface.

3.4 CLEANING

- A. Remove debris resulting from completion of coating operation from the project site.

3.5 PROTECTION

- A. After completion of application, do not allow traffic on coated surfaces for a period of at least 48 to 72 hours at 75°F. and 50% R.H., or until completely cured.

END OF SECTION

The information, data, and suggestions herein are believed to be reliable, based on Manufacturer's knowledge and experience. However, Manufacturer does not guarantee the result to be obtained in the Buyer's process. With regard to those products described herein that are manufactured by Manufacturer, Manufacturer warrants that the standards and qualities of such products will not vary by more than 10% from the tested results set forth in the Product Data Sheets associated with such products. **MANUFACTURER HEREBY EXPRESSLY DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY AND/OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE.** Buyer must make its own determination of the suitability of any product for its use, whether such product is used alone or in combination with other materials. **To the extent any of Manufacturer's products is proven to be defective, Buyer's sole remedy shall be limited to the replacement of such defective product, exclusive of any costs of labor. MANUFACTURER SHALL NOT BE LIABLE OR OBLIGATED FOR ANY LOSS OR CONSEQUENTIAL OR OTHER DAMAGE INCURRED DIRECTLY OR INDIRECTLY BY BUYER OR ANY OTHER PERSON OR ENTITY THAT ARISES IN ANY WAY IN RELATION TO ANY OF MANUFACTURER'S PRODUCTS.** Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority of the owner of the patent. No Applicator is or should be viewed as an employee or agent of Manufacturer. AutoGardSBGS.indd

NEOGARD Div. of JONES-BLAIR

2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com