



CHEMICAL RESISTANCE CHART

Rating Key: 0 - No Effect 1 - Stains/Dulls 2 - Blisters 3 - Lifts Film

<u>Chemical</u>	<u>Rating</u>	<u>Chemical</u>	<u>Rating</u>
Acetic Acid (98%)	3	Methylpyrrolidione	2
Acetic Acid (36%)	2	Mineral Spirits	0
Acetic Acid (20%)	2	Motor Oil	0
Acetic Acid (10%)	1	Mustard	0*
Ammonia (28%)	0	Nitric Acid (30%)	2
Blood	0	Nitric Acid (10%)	1
Brake Fluid	0-1	Oleic Acid	1-2
Butyl Alcohol	1-2	Phenol	2
Butoxyethanol	2	Phosphoric Acid (25%)	2
Butoxyethylacetate	2	Potassium Hydroxide (25%)	0
Butylacrylate	1	Propylene Glycol	0
Calcium Chloride (10%)	0	Skydrol	1
Chromic Acid (2%)	1	Sodium Hypochlorite (10%)	1
Citric Acid (6%)	1-2	Sodium Hydroxide (50%)	0
Citric Acid (25%)	1-2	Sodium Hydroxide (25%)	0
Citric Acid (50%)	1-2	Solvent 100	1
Citric Acid (70%)	1-2	Sulphuric Acid (96%)	2
Diacetone Alcohol	1	Sulphuric Acid (50%)	1
Diesel Fuel	0	Sulphuric Acid (20%)	1
Ethyl Acetate	1	Sulphuric Acid (10%)	1
Ethyl Alcohol	1	Tall Oil Fatty Acid	2
Ethylene Glycol	0	Urine	0*
Formic Acid (38%)	2	Vegetable Oil	0
Gasoline	0	Vinegar	1
Isopropyl Alcohol	0	Xylene	1
Jet Fuel	0		
Ketchup	0		
Lactic Acid (85%)	0-1		
Lactic Acid (50%)	1		
Lactic Acid (20%)	1		
Hydrobromic (48%)	1		
Hydrochloric Acid (37%)	1		
Hydrochloric Acid (15%)	0		
Hydrochloric Acid (5%)	0		
Hydrofluoric Acid (48%)	2		
Hydrofluoric Acid (24%)	2		
Methylisobutyl Ketone	0		

***Note: Staining is possible with mustard and urine on white and clear systems.**

Manufacturer warrants that the standards and qualities of the product described herein will not vary by more than 10% from the tested results set forth above. **MANUFACTURER HEREBY EXPRESSLY DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY AND/OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE.** Buyer must make its own determination of the suitability of any product for its use, whether such product is used alone or in combination with other materials. **To the extent this or any of Manufacturer's products is proven to be defective, Buyer's sole remedy shall be limited to the replacement of such defective product, exclusive of any costs of labor. MANUFACTURER SHALL NOT BE LIABLE OR OBLIGATED FOR ANY LOSS OR CONSEQUENTIAL OR OTHER DAMAGE INCURRED DIRECTLY OR INDIRECTLY BY BUYER OR ANY OTHER PERSON OR ENTITY THAT ARISES IN ANY WAY IN RELATION TO THIS OR ANY OF MANUFACTURER'S OTHER PRODUCTS.** Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority of the owner of the patent. No Applicator is or should be viewed as an employee or agent of Manufacturer. 05162011/70714-70715CRC.indd

NEOGARD Div. of JONES-BLAIR

2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com