

SKYGARD MD MEDIUM DUTY

Aviation Hangar Floor System - Chemical and UV Resistance System



For: Medium to large
aircraft hangar floors,
Commercial,
FBO, & Military



NEOGARD[®]
CONSTRUCTION COATINGS

Chemical and UV Resistance System




Use:

Medium to large aircraft hangar floors,
Commercial, FBO, Military

Features:

- 36 mils DFT
- High reflectivity
- Excellent wear resistance
- Excellent traction
- Two products, 4 coats
- VOC compliant
- Multiple colors available
- Tint ability
- Smooth or light texture

- Standard Colors*



WHITE



LIGHT GRAY



GRAY

* Colors shown may vary from actual product mixtures. Where color matching is critical, an applied sample is recommended. Custom colors are available at an additional cost. Minimum quantities and additional lead times are required for custom colors.

Standard flooring colors will vary by product. Consult NEOGARD® for further information.

Physical Properties	70714/70715	70805/7952	70815/70816
Material	Primer/Base Epoxy	Std Top coat	Ultra High Solids Top Coat
Compressive Strength	25,300 psi	n/a	n/a
Tensile Strength	3,700 psi	4,000 psi	4,800 psi
Elongation	25%	30%	40%
Taber Abrasion	25 mg	40 mg	5 mg
Mix Ratio by Volume	2:1	2:1	1:1
Volume Solids (mixed)	100%	62.6% (mixed)	89%
VOC (mixed)	< 5 g/l	340 g/l (mixed)	95 g/l
Pot Life at 75°F	30 minutes	4-5 hrs.	20 - 25 minutes
Touch Up Time at 75°F	20 minutes	25 minutes	10 minutes
Tack Free Time at 75°F	8 to 9 hrs.	4-6 hrs.	4 hrs.
Dry to Walk on at 75°F	24 hrs.	24 hrs.	8 hrs.
Fungus & Bacteria Resist	No Support of Growth Under TT-P-34	No Support of Growth Under TT-P-34	No Support of Growth Under TT-P-34

Chemical	70714/70715	70805/7952	70815/70816
Brake Fluid	0-1	0-1	0
Calcium Chloride 10%	0	0	0
Diacetone Alcohol	1	0	0-1
Diesel Fuel	0	0	0
Ethyl Acetate	1	1	1
Ethyl Alcohol	1	0	0
Ethylene Glycol	0	0	0
Gasoline	0	0	0
Isopropyl Alcohol	0	0	0
Jet Fuel	0	0	0
Ketchup	0	0	0
Hydrochloric Acid 37%	1	0	0-1
Methylisobutyl Ketone	0	0	0
Mineral Spirits	0	0	0
Motor Oil	0	0	0
Mustard	0	0	0-1
Skydrol	1	0	0
Sodium Hydroxide (50%)	0	0	1
Solvent 100	1	0	0-1
Sulphruic Acid (50%)	1	0	0-1
Urine	0	0	0
Xylene	0-1	0	0

Rating Key:			
0 - No Effect	1 - Stains/Dulls	2 - Blisters	3 - Lifts Film



NEOGARD®
CONSTRUCTION COATINGS

214-353-1600
FAX: 214-353-1766
P.O. Box 35286
2728 EMPIRE CENTRAL
DALLAS, TX 75235-4409
NEOGARD®, A Division
of JONES-BLAIR® Company

www.neogard.com
www.jones-blair.com
NFLSHM-HOUT-041309
PRINTED IN USA